

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C04B 41/71, E21D 11/10, 11/38, E04B 1/66 // C04B 111/27	A1	(11) International Publication Number: WO 98/24738 (43) International Publication Date: 11 June 1998 (11.06.98)
(21) International Application Number: PCT/EP97/06732 (22) International Filing Date: 1 December 1997 (01.12.97) (30) Priority Data: 9625163.2 4 December 1996 (04.12.96) GB (71) Applicant (for all designated States except US): MBT HOLD- ING AG [CH/CH]; Vulkanstrasse 110, CH-8048 Zürich (CH). (72) Inventors; and (75) Inventors/Applicants (for US only): DISCHÖ, Karoly [CH/CH]; Weiherstrasse 14, CH-8307 Effretikon (CH). OPPLIGER, Max [CH/CH]; Burgfeldermattweg 59, CH-4123 Allschwil (CH).		(81) Designated States: AU, BR, CA, CN, JP, SG, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>no claim agt.</i>
(54) Title: CEMENT STRUCTURE CONTAINING A WATERPROOFING LAYER (57) Abstract A process of providing a waterproof concrete structure comprising the steps of: (a) providing a layer of a concrete composition on a support; (b) spraying on to this concrete composition a waterproofing layer; and (c) applying to the waterproofing layer a further layer of a concrete composition; characterised in that the waterproofing layer is provided by a composition which comprises an aqueous dispersion of coalescable particles of thermoplastic polymer. The method is useful in the waterproofing of tunnel linings.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

CEMENT STRUCTURE CONTAINING A WATERPROOFING LAYER

This invention relates to membranes for use in the waterproofing of cementitious structures.

5

In the provision of cementitious structures, such as the building of tunnels by boring or excavating and then shotcreting, there is often a need to provide waterproofing. This is typically achieved either by providing drainage or by firstly injecting fissures in the rock with materials such as cement, microcement and reactive resin, this being followed by a
10 layer of shotcrete. To this layer is applied a waterproof membrane, and to this membrane is applied a further layer of shotcrete or in situ concrete. The waterproof membrane is typically a prefabricated sheet of waterproof polymeric material which is anchored in place by, for example, anchoring bolts. The result is thus a "sandwich" construction. Sometimes there may be applied by *in situ* placing or spraying a further layer of concrete
15 with reinforcing (fibres or mesh), or this reinforcing may be incorporated into the final concrete coating.

The labour intensity of such a method, plus the fact that the existing membranes have not been wholly satisfactory, particularly with respect to leaking, has led to the search for
20 alternatives. Recently, attempts have been made to spray on a suitable membrane. These have used a two-pack polyurethane material, but these have suffered from drawbacks such as complicated application, toxicity problems (from the isocyanate curing agents), bonding problems to wet shotcrete and inhibition of polyurethane formation because of high tunnel humidity has prevented the obvious potential benefits of such a method being
25 realised.

It has now been found that it is possible to provide a suitable membrane by means of a method which avoids most or even all of the drawbacks hereinabove mentioned. There is therefore provided, according to the present invention, a process of providing a
30 waterproof concrete structure comprising the steps of

- (a) providing a primary layer of a concrete composition on a support;
- (b) spraying on to this concrete composition a waterproofing layer; and
- (c) applying to the waterproofing layer a layer of a concrete composition;

CONFIRMATION COPY

characterised in that the waterproofing layer is provided by a composition which comprises as a binder an aqueous dispersion of coalescable particles of thermoplastic polymer.

- 5 The invention further provides a waterproof sandwich concrete structure comprising two layers of concrete separated by a coherent intermediate polymeric layer whose binder is coalesced particles of thermoplastic polymer.

By "support" is meant a untreated, water-permeable surface to which the waterproof
10 concrete structure of this invention is applied. This will usually be a rough rock surface, but it may equally well be a man-made surface, such as a ceiling. The concrete compositions of steps (a) and (c) hereinabove described may be the same or different. In the case of the concrete composition of the primary layer (a), the scope of this term is considered to encompass not only simple concrete compositions (cold sprayed or
15 prefabricated) but also such known variants as concrete followed by a levelling or smoothing layer of a spray mortar (up to 4mm).

By "binder" is meant a material which on drying forms a coherent, continuous film and by thermoplastic" is meant a material which does not react to form a crosslinked
20 structure. By "coalescable particles" is meant particles of a film-forming suspension or emulsion which, on the removal of the continuous medium in which they are dispersed, at least partially merge to form a continuous, coherent film. The polymer dispersions which are useful in this invention are thus similar in nature to the film-forming aqueous dispersions which are used, for example, as film-forming media in aqueous "emulsion"
25 household paints. Included in this definition of "binder" are compositions which include thermoplastic coalescable particles and cement.

The aqueous dispersion of coalescable thermoplastic polymer particles may be chosen from a wide range of materials known to the art, the nature of the polymer itself being
30 unimportant. Thus, for example, suitable polymers include polyurethanes, polyesters, vinyls and acrylics. Particularly suitable polymers are addition polymers derived from ethylenically-unsaturated monomers by addition polymerisation. Particularly suitable materials within this group are those which have a glass transition temperature (T_g) such

that they remain in the "rubbery" condition under conditions of use, those having a degree of elastomeric properties being particularly desirable. It is preferred that the T_g be below 15°C , more preferably below -15°C . The weight solids contents of such dispersions typically lie within the range of 30-60%. Specific examples of suitable materials include polyurethanes, styrene-butadiene copolymers, ABS (acrylonitrile-butadiene-styrene) polymers, acrylonitrile-butadiene copolymers, styrene-acrylic copolymers, polysulphide dispersions, polyurethane-acrylic dispersions, polyisoprene and PVC latexes and copolymers of vinyl chloride and/or vinyl acetate with acrylic monomers such as (meth) acrylic acid and esters thereof. Materials such as bitumen emulsions may be used in conjunction with these materials, but as such materials do not coalesce, they should not comprise more than 50% by weight solids of the binder. This list is not exhaustive, and the skilled person equipped within the concept of this invention will readily be able to identify other suitable materials. Many such materials are available commercially and examples of suitable commercial materials include those sold by BASF AG. under the trade mark "Acronal" and those sold by Synthomer under the trade mark "Synthomer".

In addition to the aqueous dispersion, the composition may include other ingredients. One especially useful ingredient is filler. This not only "extends" the composition, but also roughens the surface, thus providing a "key" for a subsequently applied cementitious composition. Its presence is preferred. Typical examples of suitable fillers include quartz sand and quartz flour of average diameters in the range of from 0.04-1.5mm, as well as dolomite, talc, mica, barytes, iron oxide, titanium dioxide, rubber and plastics granules, lightweighted aggregates and glassy furnace residues such as "holospheres". Fibres of steel, glass or polymeric material can also be used, preferred examples of polymeric fibre being those of thermoplastic material, especially polyethylene and polyacrylonitrile, preferably with length of from 0.2-12mm and surface area of from $6-8\text{M}^2/\text{g}$.

There may also be added to the compositions of this invention standard ingredients in art-recognised quantities. Typical examples of additives whose presence may be beneficial include flow-enhancing agents, defoamers, dispersants, colouring materials, wetting agents, rheology modifiers and catalysts.

When there is no filler present, a composition for use in this invention may comprise 100% of dispersion. When desired, additives may comprise up to 5%, preferably 0.1-5% by weight (calculated on active ingredients of additive per weight of liquid dispersion).

- When filler is present (the preferred case), the composition preferably comprises 20-80% (more preferably 30-50%) by weight dispersion, 79.9-15% (more preferably 69.9-15%) by weight filler, and 0.1-5% by weight additive(s).

The weight of dispersion is the weight of the liquid dispersion and the weight of the additive is the weight of active ingredient.

10

- The composition may be applied by spraying to a primary layer concrete. This is preferably shotcrete, but it may be other suitable cementitious compositions, such as polymer concrete. The membrane layer applied may vary in thickness, depending on the material used, the conditions of application and the properties (such as crack bridging ability) desired, but as a general rule it should have a thickness of 2-15mm, preferably 2-6mm. The application may be done in a single spraying pass or in several passes. To this sprayed composition is applied a further layer of cementitious composition, preferably shotcrete applied by spraying. The result is a "sandwich" construction. The preferred ways in which such a sandwich construction may be created are shown below:

20

	Variation		
	A	B	C
1st. layer	shotcrete (typically 50-250mm thick)	prefabricated concrete elements (200-500mm)	shotcrete
2nd. layer	2-10mm thick membrane (Example 2 composition)	2-5mm thick membrane (Example 4 composition)	membrane (5-10mm)
3rd. layer	shotcrete (typically 50-250mm thick)	shotcrete or concrete placed <i>in situ</i>	poured concrete or concrete placed <i>in situ</i>

The preferred variation is the A variation. Included in the first layer is the possibility that there may be applied thereto a levelling mortar, this being from 2-15mm thick. The membrane can be sprayed on to the concrete 1-90 days after the application of the concrete. If spraying is consistent within 3 days after concrete application, there is the additional advantage that the water in the dispersion can help with the cement hydration. When the concrete of the first layer has been in place for a longer time (3-60 days), it may be necessary to wash the surface with water. This removes only residues and prewastes the surface, giving better membrane adhesion. As previously mentioned, it can be applied in a single pass or in a number of passes with suitable pauses to allow drying and/or hardening. In the multi-layer approach, one or more of the sprayed layers may include reinforcing fibres of glass, steel, ceramic or polymer; alternatively, reinforcing in the form of mesh or roving can be applied to still-wet membrane and the reinforcing then covered by a further layer of membrane.

The structure thus formed has excellent waterproofing properties, coupled with excellent water vapour permeability, thus allowing any trapped water to escape through the membrane and avoiding any interfacial failure. In addition, it is durable, safe and easy to apply and relatively inexpensive.

The invention is further described with reference to the following non-limiting examples in which all parts are expressed by weight.

A number of compositions are prepared by blending together the following combinations of ingredients:

25

Example 1

polymer dispersion ¹	30	parts
barytes	27	parts
calcium carbonate	42.5	parts
30 titanium dioxide	0.5	parts

1. styrene-acrylic ester copolymer emulsion 50% solids by weight ("Acronal" (trade mark) S361 (ex BASF))

Example 2

	polymer dispersion ²	40	parts
	calcium carbonate	55	parts
	defoamer ³	2	parts
5	dispersant ⁴	1	parts
	pigment ⁵	2	parts

2. "Acronal" S361

3. "BYK-035" ex Byk Chemie, a mixture of hydrophobic components in a paraffin-
10 based mineral oil

4. "Pigment dispersant A" ex BASF, a 20% aqueous solution of ammonium
polyacrylates

5. black iron oxide "Bayferrox" (trade mark) 316 ex Bayer

15 **Example 3**

	polymer dispersion ⁶	50	parts
	barytes	48	parts
	defoamer ⁷	1	parts
	dispersant ⁸	1	parts

20

6. "Acronal" 6210 (styrene-acrylic ester copolymer)

7. "Agitan" (trade mark) 731 ex Münzing Chemie GmbH. a modified
organopolysiloxane

8. "Pigment dispersant A".

25

Example 4

	polymer dispersion ⁹	40	parts
	calcium carbonate	32	parts
	defoamer ¹⁰	2	parts
30	pigment dispersant ¹¹	0.5	parts
	pigment ¹²	0.5	parts
	barytes	22	parts
	acrylic fibres 0.5mm long	1	parts

9. "Acronal" S361
10. BYK-035
11. "Pigment dispersant A"
5 12. red iron oxide "Bayferrox" 105M

Example 5

polymer dispersion¹³ 60 parts
calcium carbonate 40 parts

10

13. styrene-butadiene-acrylic ester copolymer emulsion 53% solids ("Synthomer"
33y 20 (ex Synthomer))

Example 6

- 15 An example of a mixed system (polymer dispersion + cement)

polymer dispersion¹⁴ 55 parts
portland cement 14.8 parts
quartz sand 0.1-0.4mm 8 parts
quartz flour 22 parts

- 20 polyethylene fibres,
average length 0.2mm 0.2 parts

14. acrylic ester-acrylonitrile copolymer emulsion 55% solids by weight ("Acronal"
DS 6137X)

25

Example 7

polymer dispersion¹⁵ 35 parts
polyethylene/polypropylene fibres 1.5 parts
30 barytes 48 parts
hollow glass spheres 10 parts
water 5.5 parts

Testing of compositions

The compositions according to Examples 2 and 3 are sprayed on to concrete plates of dimensions 500x500x40mm at a film build of 2mm and tested. The results are shown in

5 Table 1.

Table 1

Property measured	Result	
	Example 2	Example 3
bonding strength (N/mm ²) ¹	0.6	0.6
strain at rupture (%) ²		
- at room temperature	250	140
- at -20°C	63	40
stress (N/mm ²) ³ at rupture		
- at room temperature	0.8	1.7
- at -20°C	8.5	7.7
tear propagation (N/mm) ⁴ (at room temperature)	11	12
water absorption (%) ⁵ (3d at room temperature)	5	10

1. measured according to DIN/ISO 4624
 - 10 2. measured according to DIN 53504
 3. measured according to DIN 53504
 4. measured according to DIN 53515
 5. measured according to DIN 62617
- 15 The crack-bridging ability of the compositions of the invention depends on the thickness of the membrane deposited. The excellent crack-bridging ability of the compositions according to the invention is demonstrated by the testing of the composition of Example 2 on a universal testing machine. In this method, a cylindrical specimen of concrete (diameter 50mm, thickness 30mm) is stretched on the machine at a rate such that there is
- 20 generated in the concrete a continuous transverse crack at a rate of 0.1mm/min. The

crack width in the concrete is measured at the point when there occurs in the membrane a crack extending completely through it. The results are shown in Table 2.

Table 2

membrane thickness (mm)	test temperature (°C)	crack width in concrete (mm) at through cracking point in membrane
0.7	20	1.5
	-20	1.0
1.7	20	2.7
	-20	2.1
2.3	20	4.1
	-20	3.6

Claims:

1. A process of providing a waterproof concrete structure comprising the steps of
 - (a) providing a primary layer of a concrete composition on a support;
 - 5 (b) spraying on to this concrete composition a waterproofing layer; and
 - (c) applying to the waterproofing layer a further layer of a concrete composition;characterised in that the waterproofing layer is provided by a composition which comprises an aqueous dispersion of coalescable particles of thermoplastic
10 polymer.
2. A process according to claim 1, wherein the thermoplastic polymer is an addition polymer produced by polymerisation of ethylenically-unsaturated monomer.
- 15 3. A process according to claim 1 or claim 2, wherein the polymer has a glass transition temperature (T_g) such that it remains in the "rubbery" condition under conditions of use.
4. A process according to any one of claims 1-3, wherein the polymer has a degree of
20 elastomeric properties.
5. A process according to any one of claims 1-4, wherein the T_g of the polymer is below 15°C
- 25 6. A process according to claim 6, wherein the T_g is below -15°C .
7. A process according to any one of claims 1-6, wherein the composition comprises either or both of fillers and additives.
- 30 8. A process according to claim 7, wherein the composition consists of 20-80% by weight dispersion, 79.9-15% by weight filler(s), and 0.1-5% by weight additive(s).

9. A waterproof sandwich concrete structure comprising two layers of concrete separated by a coherent intermediate polymeric layer whose binder is coalesced particles of thermoplastic polymer.

5

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/06732

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C04B41/71 E21D11/10 E21D11/38 E04B1/66 //C04B111/27

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B E21D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	PATENT ABSTRACTS OF JAPAN vol. 018, no. 465 (M-1665), 30 August 1994 & JP 06 146798 A (NIPPON KENSETSU KIKAIKA KYOKAI;OTHERS: 01), 27 May 1994, see abstract ---	1-9
Y	EP 0 460 744 A (C-CURE CHEMICAL CO INC) 11 December 1991 see page 3, line 34 - line 53 see examples 1,6,7 see claims 1-20 ---	1-9
A	PATENT ABSTRACTS OF JAPAN vol. 018, no. 291 (C-1208), 3 June 1994 & JP 06 057060 A (TONEN CHEM CORP), 1 March 1994, see abstract -----	1-9

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

30 March 1998

Date of mailing of the international search report

06/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
 Fax: (+31-70) 340-3016

Authorized officer

Rosenberger, J

INTERNATIONAL SEARCH REPORT
Information on patent family members

International Application No

PCT/EP 97/06732

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0460744 A	11-12-91	AU 647476 B	24-03-94
		AU 7728891 A	12-12-91
		CA 2043094 A,C	07-12-91
		DE 69126921 D	04-09-97
<hr/>			

THIS PAGE BLANK (USPTO)